



0845 034 6012  
info@juta.co.uk  
www.juta.co.uk

## Product: GP<sup>®</sup> PRIMER

JUTA GP<sup>®</sup> (quick drying) PRIMER is a cold applied bituminous solution designed to penetrate and seal porous surfaces prior to the application of covering materials. Conforms to BS Code of Practice 144, Part 3.

### Uses

GP<sup>®</sup> Primer seals porous substrates and encourages the adhesion of bituminous waterproofing systems and sheet coverings. It may be applied successfully to a wide range of surfaces:

- CONCRETE
- ASBESTOS CEMENT
- SLATE
- METALS (mild steel, Zinc, Lead)
- LIGHTWEIGHT CONCRETE SCREEDS

GP<sup>®</sup> PRIMER is available in 5 Litre and 25 litre containers.

### Product Data

GP <sup>®</sup> PRIMER	
Colour	Black
<u>Coverage</u>	
Metal Surfaces	6 – 11 m <sup>2</sup> per litre
Concrete	3 – 4 m <sup>2</sup> per litre
Bituminous	5 – 8 m <sup>2</sup> per litre
Drying time	Allow to dry completely before subsequent installation begins.  Drying time is dependent on ambient air temperature, atmospheric conditions and porosity of the substrate.  Average drying time at 20°C is between 2 – 6 hours.

### Method of Use

#### Apply by brush or spray

Surfaces should be clean, ie. Free from all oil, grease, dirt, dust and loose debris. On metal surfaces all loose rust should be removed using a wire bristled brush and where advanced signs of corrosion are evident these areas should initially be treated with a rust inhibitor. Surfaces should preferably be dry although GP<sup>®</sup> PRIMER will adhere to damp but not wet surfaces. GP<sup>®</sup> PRIMER should be applied evenly across the surface in one generous coating.



Technical data



☎ 0845 034 6012  
✉ [info@juta.co.uk](mailto:info@juta.co.uk)  
🌐 [www.juta.co.uk](http://www.juta.co.uk)

### STORAGE

Storage life indefinite in tightly sealed, undamaged containers.

### HEALTH AND SAFETY

Refer to Material Safety Data Sheet (MSDS) for a full list of hazards.

### ADDITIONAL INFORMATION

For additional information or assistance, please contact JUTA UK directly.

